

PRODUCT INFORMATION

RECLAIMED ALUMINA TYPE SSB

Description: Non-metallic, synthetic fine blasting medium made of high quality grinding disks and corundum powder; a mixture of normal and special corundum.

Applications: Descaling, cleaning and deburring of steel, brass and machine parts.

Use: Pressure blasting



SIEVING RANGES special grain sizes upon request

FEPA	my	FEPA	my
16	1000 - 1410	70	177 - 250
20	841 - 1190	80	149 - 210
24	595 - 841	90	125 - 177
36	420 - 595	100	105 - 149
40	354 - 500	120	88 - 125
46	297 - 420	150	63 - 105
54	250 - 354	180	53 - 88
60	210 - 297	220	44 - 74

CHEMICAL COMPOSITION

Al ₂ O ₃	85.8%	SiC	2,75%
SiO	8,9%	CaO	1,25%
TiO ₂	0,95%	MgO	1,25%
FeO	0,35%		

TECHNICAL DATA

Specific weight	approx. 4.0 g/cm ³
Bulk weight	approx. 1.5 - 1.7 kg/l
Hardness according to Mohs:	approx. 8 - 9